



NovaGrip® 30 14.5 OZ GEOMEMBRANE



NOVA GRIP®

PRODUCT DESCRIPTION

AquaMaster NovaGrip 30 is a highly puncture resistant liner incorporating a textured surface for slip protection and increased interface friction.

RECOMMENDED APPLICATIONS


Canal Lining, Well Pads, Containment Liners

PRODUCT DIMENSIONS

Cores 4 inch I.D. or 5 inch I.D. available (10 cm or 13 cm)
Width Up to 150 in (381 cm) (-0, +0.5) as ordered
Length Minimum 250 yds/roll (229 m); up to 500 yds/roll (457 m)

PRODUCT SPECIFICATIONS

Weave Woven black HDPE scrim
Coating LDPE, 2.4 mil average each side (57 g/m²/side)
Color Black
Weight 14.5 oz/yd² (492 g/m²) ± 5 %



These values are typical data and are not intended as limiting specifications.

PERFORMANCE PROPERTIES

The following data are typical values based on ASTM standard tests. This data should not be considered specification.

Thickness ASTM D1777	30 mil (0.68 mm) ± 10% (without texture)
Asperity Height ASTM D7466	>20 mil (>0.5mm)
Grab Tensile (N) ASTM D7004	MD 420 lb (1868) TD 315 lb (1401)
Strip Tensile (N/5cm) ASTM D7003	MD 250 lb/in (2189) TD 190 lb/in (1664)
Tongue Tear—large scale (N) ASTM D5884	MD 80 lb (356) TD 90 lb (400)
Mullen Burst ASTM D751	580 psi (4002 kPa)
MVTR ASTM E96 Proc. BW	0.12 g/m ² · 24hr (0.017 perms)
Hydraulic Conductivity (Permeability) Calculated from MVTR	7.68 x 10 ⁻¹⁵ cm/s
Hydrostatic Resistance ASTM D751	370 psi (2549 kPa)
Puncture Resistance ASTM D4833	160 lb (712 N)
CBR Static Puncture ASTM D6241	985 lb (4373 N)
Carbon Black Content ASTM D4218	3 %
Dimensional Stability ASTM D1204	MD -1.3% TD -0.7%
Low Temperature Flex ASTM D2136	MD & TD: Pass @ -65°C (-85°F)
HP-OIT ASTM D5885 (Measured on coating formulation)	1536 minutes

MD = Machine Direction. TD = Transverse Direction.

Please contact your IPG representative for warranty details.



These values are typical data and are not intended as limiting specifications.

While we believe them to be reliable, the statements and information herein are only for general guidance and are not warrants or guarantees for accuracy and completeness. The user must, by test or otherwise, determine suitability for this purpose. There is no warranty of fitness for a particular purpose. Our standard term and conditions of sale apply exclusively to all orders, and all liability for damages of any kind, including consequential, exceeding purchase price is excluded. No one is authorized by us to make oral warranties. We reserve the right to make changes without notice or obligation in our products and publications.